

[illegible]

- 5

- 10

- 15

- 20

- 25

- 30

9. Method according to claim 8 wherein said mineral oil is present in said fluoroelastomer composition in an amount of 0.25 to 15 parts by weight for 100 parts by weight of fluoroelastomer.
- 5 10. Method according to claim 8 wherein said mineral oil is at least partially adsorbed on a carrier.
11. Method according to claim 10 wherein said carrier comprises particles capable of adsorbing said mineral oil.
- 10 12. Method according to claim 11 wherein said particles are selected from the group consisting of carbon black and inorganic particles.
13. Method according to any of claims 8 to 12 wherein said fluoroelastomer composition further comprises a wax.
- 15 14. Method according to claim 13 wherein said wax is a vegetable wax and is contained in said fluoroelastomer composition in an amount of less than 2 parts by weight per 100 parts by weight of fluoroelastomer.
- 20 15. Method according to any of claims 8 to 14 wherein said fluoroelastomer composition comprises a vulcanization system and wherein said method includes the step of vulcanization.
- 25 16. Fluoroelastomer composition comprising a fluoroelastomer and a mineral oil, said composition being free of vegetable wax or containing vegetable wax in an amount of less than 2 parts by weight per 100 parts by weight of fluoroelastomer.
- 30 17. Fluoroelastomer composition according to claim 16 wherein said fluoroelastomer composition is free of any wax or contains a total amount of vegetable and non-vegetable wax of less than 2 parts by weight per 100 parts by weight of fluoroelastomer.

[illegible]

19. Fluoroelastomer composition according to claim 18 wherein said carrier comprises particles
5 capable of adsorbing said mineral oil.

20. Fluoroelastomer composition according to claim 19 wherein said particles are selected from the group consisting of carbon black and inorganic particles.

21. Fluoroelastomer composition according to any of claims 16 to 20 wherein said mineral oil is comprised in the fluoroelastomer composition in an amount of 0.25 to 15 parts by weight for 100 parts by weight of fluoroelastomer.

22. Fluoroelastomer composition according to any of claims 16 to 21 further comprising a
15 vulcanization system.

23. Method of making a fluoroelastomer composition having improved flow characteristics when processed, said method comprising the steps of blending together a mineral oil and a fluoroelastomer to obtain a fluoroelastomer composition that is free of vegetable wax or alternatively to blend together a mineral oil, a fluoroelastomer and a vegetable wax to obtain a fluoroelastomer composition that contains a vegetable wax in an amount of less than 2 parts by weight for 100 parts by weight of fluoroelastomer.

24. Method according to claim 23 wherein said mineral oil is adsorbed on a carrier when
25 blended with said fluoroelastomer.

25. Method according to claim 24 wherein said carrier comprises particles capable of adsorbing said mineral oil.

30 26. Method according to claim 25 wherein said particles are selected from the group consisting of carbon black and inorganic particles.